



**QINGDAO SANHUAN COLORCHEM CO., LTD.**

RM2301, BUILDING 4, PENGLINANHUA Plaza,  
12 LIAOYANG EAST ROAD, QINGDAO, CHINA  
EMAIL: michael@cncolorchem.com

TEL: 0086 532 88978177/88978188  
FAX: 0086 532 88962988/88967877  
WEBSITE: www.cncolorchem.com

---

## **TECHNICAL DATA SHEET**

### **Acid Black 26**

#### **1. Product Name**

C.I. No.: ACID BLACK 26  
CAS Number: 6262-07-3  
Chemical Formula: C<sub>32</sub>H<sub>21</sub>N<sub>5</sub>Na<sub>2</sub>O<sub>7</sub>S<sub>2</sub>  
Molecular Weight: 697.65

#### **2. Physical, Chemical and Resistance Properties**

Appearance: Black Powder  
Shade: Similar to Standard  
Tinting strength(%): 100±3

The dyeing fastness in wool fabric (Grade) :

Light Fastness Fading: 6  
Soaping Fastness Fading(40°C): 4  
Soaping Fastness Staining(40°C): 5  
Water Logging Fastness Fading: 4  
Water Logging Fastness Staining: 4~5  
Carbonization Fading: 4  
Perspiration Fastness Fading (Acid) : 4  
Perspiration Fastness Staining (Acid) : 4~5  
Perspiration Fastness Fading(Alkali): 4~5  
Perspiration Fastness Staining(Alkali): 4~5  
Dry Rubbing Staining: 5  
Seawater Logging Fastness Fading: 4~5  
Seawater Logging Fastness Staining: 4~5  
Fulling Milling Fading (Acid) : 4~5  
Fulling Milling Staining (Acid) : 4  
Fulling Milling Fading(Alkali): 4~5  
Fulling Milling Staining(Alkali): 5  
Crabbing Fading (70°C) : 4~5  
Crabbing Staining (70°C) : 4~5  
Ironing Fastness Fading: 4~5



## **QINGDAO SANHUAN COLORCHEM CO., LTD.**

RM2301,BUILDING 4,PENGLINANHUA Plaza,  
12 LIAOYANG EAST ROAD, QINGDAO,CHINA  
EMAIL: michael@cncolorchem.com

TEL:0086 532 88978177/88978188  
FAX:0086 532 88962988/88967877  
WEBSITE: www.cncolorchem.com

---

Chlorination Fading:4

Decatizing Fading:4~5

Alkali resistance:4

### **3. Application**

Dyeing for Wool, Nylon, Silk and Blend,Coloring for Paper and Leather

### **4.Package**

Packed in 25kgs Carton