



QINGDAO SANHUAN COLORCHEM CO., LTD.

RM2301,BUILDING 4,PENGLINANHUA Plaza,
12 LIAOYANG EAST ROAD, QINGDAO,CHINA
EMAIL: michael@cncolorchem.com

TEL:0086 532 88978177/88978188
FAX:0086 532 88962988/88967877
WEBSITE: www.cncolorchem.com

TECHNICAL DATA SHEET

Basic Violet 14

1. Product Name

C.I. No.: BASIC VIOLET 14

CAS Number: 632-99-5

Molecular Formula: C₂₀H₂₀ClN₃

Molecular Weight: 337.85

2. Physical, Chemical and Resistance Properties

Appearance: Yellow Green Crystalloid Block

Shade: Similar to Standard

Tinting strength%: 100±3

insolubility in water%: ≤0.5

The dyeing fastness in cotton fabric (Grade) :

Light Fastness:1~2

Soaping Fastness Fading:3~4

Soaping Fastness Staining:4

Water Logging Fastness Fading:3~4

Water Logging Fastness Staining:3

Ironing Fastness: 1~2

Perspiration Fastness Fading: 3

Perspiration Fastness Staining:2~3

Dry Rubbing Fastness: 4

Wet Rubbing Fastness:4

Sulphuric Acid Resistance:3~4

Acetic Acid Resistance:1

Sodium Carbonate Resistance:4~5

The dyeing fastness in acrylic fabric (Grade) :

Light Fastness:5~6

Soaping Fastness Fading:4

Ironing Fastness: 4

Perspiration Fastness Fading: 4



QINGDAO SANHUAN COLORCHEM CO., LTD.

RM2301,BUILDING 4,PENGLINANHUA Plaza,
12 LIAOYANG EAST ROAD, QINGDAO,CHINA
EMAIL: michael@cncolorchem.com

TEL:0086 532 88978177/88978188
FAX:0086 532 88962988/88967877
WEBSITE: www.cncolorchem.com

Dry Rubbing Fastness: 4~5

Wet Rubbing Fastness:3~4

Dryclean:4~5

3. Application

Dyeing for Silk, Wool, Acrylic, Tannin coal dyed cotton and Cotton

Coloring for Paper, Leather, Feather, Flax and Wood

4.Package

Packed in 25kgs Drum