QINGDAO SANHUAN COLORCHEM CO., LTD.

17 FLOOR, YUHENG BUILDING, NO.170 XUZHOU NORTH ROAD, QINGDAO, CHINA
EMAIL: michael@cncolorchem.com
TEL:0086 532 88978177/88978188
FAX:0086 532 88962988/88967877
WEBSITE: www.cncolorchem.com

TECHNICAL DATA SHEET

Pigment Yellow 14

1. Product Name

Trade Name: Pigment Yellow 14 (2GS-SS)

C.I.: Pigment Yellow 14

C.I. No.: 21095

CAS No.: 5468-75-7

EINECS No.: 226-789-3

Chemical Formula: $C_{34}H_{30}Cl_2N_6O_4$

Molecular weight: 657.55

2. Physical, Chemical and Resistance Properties

Appearance: Yellow Powder

Shade: Similar to Standard

Tinting Strength (%): 100±5

Moisture (%): ≤2.0

Water Soluble Matter (%): ≤1.5

Oil Absorption (ml/100g): 30~40

Electric Conductivity (us/cm): ≤500

Fineness (80mesh) (%): ≤5.0

PH Value: 6.0~7.0

Acid Resistance(5=excellent): 5

Alkali Resistance(5=excellent): 5

Alcohol Resistance(5=excellent): 4

Heat Resistance (℃): 180

Light Fastness (8=excellent): 6

3. Application

Suggested for Solvent base ink(Surface printing ink).

4. Packing

In 25 kgs bag with pallet.